

## LIGHT WELD® 4-20508 ONE-PART UV CURING DOME COATING

### DESCRIPTION

Dymax Light Weld 4-20508 is a clear, rigid dome coating that cures in seconds upon exposure to long wave (365 nm) UV light. The clear coating has a high gloss, low profile dome with excellent adhesion to metal, glass, and many plastics. Dymax 4-20508 is best suited to doming novelty items, such as nameplates, keychains, and pens.

- **Clear, Hard, Low-Profile Dome**
- **Slick, Abrasion Resistant Surface**
- **Fast Curing**

### TYPICAL UNCURED PROPERTIES

Solvent Content	None	
Composition	100% Solids	
Appearance	Clear	
Solubility	Isopropyl alcohol, ketones, and chlorinated solvents	
Toxicity	Low	
Flash Point	>95°C (200°F)	
Density	1.0 kg/L (8.7 lbs/gallon)	
Viscosity (@ 20 rpm)	750 cP (nominal)	ASTM D-1084

### TYPICAL CURED PROPERTIES

#### *PHYSICAL*

Durometer Hardness	D80	ASTM D-2240
Gardner Color	1	
Refractive Index	1.50	

### TYPICAL CURE DATA

UV Light - Using 365 nm wavelength UV light <sup>[1]</sup>:

	Cure Time	Intensity <sup>[2]</sup> mW/cm <sup>2</sup>	Dymax Light-Welder® Lamps
Coating Cures, stationary lamp	15 sec	150	5000-EC
Coating Cures, conveyor	>7 ft/min	350	UVC6/12002
Coating Cures, conveyor	>5 ft/min	1000	UVC6/F300
Nominal Cure Depth (0.25 inch)	30 sec	35	2000-EC

### DISPENSING AND HANDLING ADHESIVE

Dymax 4-20508 is available in various packages such as syringes, cartridges, bottles, and pails. It may be dispensed with a variety of automatic bench-top syringe applicators or other equipment as required. Direct questions relating to dispensing and curing systems for specific applications to Dymax Technical Representatives.

Wear impervious gloves and/or barrier cream. Repeated or continuous skin contact with liquid adhesive will cause irritation and should be avoided. Do not wear absorbent gloves. Remove adhesive from skin with soap and water. Never use solvents to remove adhesive from skin or eyes.

## **STORAGE AND SHELF LIFE**

Store material in cool dark place when not in use. Do not expose to UV light or sunlight. Material may polymerize upon prolonged exposure to ambient light. Replace lid immediately after use. Product has a one-year shelf life when stored below 90°F in the original, unopened container. Refrigerated storage extends shelf life.

## **CAUTION**

For industrial use only. Avoid breathing vapors. Avoid contact with eyes and clothing. In case of contact, immediately flush with water for at least 15 minutes; get medical attention. Wash clothing before reuse. Keep out of reach of children. Do not take internally. If swallowed, induce vomiting at once and call a physician. Repeated or continuous skin contact with liquid adhesive will cause irritation and should be avoided. For specific information, refer to the product Material Safety Data Sheet.

## **NOTES**

- [1] Use of lamps that emit high levels of short wave light (for example, more than 15% 200-300 nanometer UV light) are not recommended.  
[2] Nominal intensity taken at a predetermined distance. This reading does not reflect the maximum intensity capabilities emitted from each unit.

## **intertronics**

17 Station Field Industrial Estate  
Banbury Road  
KIDLINGTON  
Oxfordshire, OX5 1JD  
Tel: 01865 842842 Fax: 01865 842172  
e-mail: [enquiries@intertronics.co.uk](mailto:enquiries@intertronics.co.uk)  
[www.intertronics.co.uk](http://www.intertronics.co.uk)

© 2000 Dymax Corporation  
MD® Medical Device Adhesives is also a registered trademark of Dymax Corporation

The data contained in this bulletin which represents typical results, is furnished for information only, and is believed to be reliable. We cannot assume responsibility for results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any product or method mentioned herein and to adopt such precautions as may be advisable for the protection of property and persons against any hazards that may be involved in the handling and use thereof. Nothing in this bulletin is to be interpreted as a representation of freedom from domination of patents owned by others or a license under a Dymax Corporation patent. We recommend that each prospective user test the proposed application before repetitive use, using the data as a guide. For specific information, refer to Material Safety Data Sheet before use.