

A total solution to high performance adhesive bonding

One stop shop technology for structural bonding of plastics

• Fully comprehensive range of structural adhesives

The Araldite® 2000 PLUS range adhesives for plastics can be used under a broad spectrum of processing and curing conditions and can meet the most demanding performance requirements. The range includes leading-edge epoxy, polyurethane and toughened acrylic technologies providing a complete solution to structural bonding.

• Broad range of easy to use packing sizes

Araldite® 2000 PLUS adhesives are available in a wide range of cartridge systems and small packs for convenient handling. These options allow the user to accurately deliver a measured quantity of adhesive with minimum wastage.

• Local availability

No matter where you are in the world, Huntsman's strong global network means Araldite® 2000 PLUS adhesives can be supplied locally. Our operations span 30 countries and are supported by an established worldwide distribution framework.

Setting the industry standard for technical support

• Comprehensive telephone technical support

Huntsman sets the standard for technical support. Its industry experts can provide advice at a local level and can rapidly respond to customer challenges.

• On site technical assistance

Our network of technical support staff can give on site demonstrations and provide expert advice to find the best solution for a range of technical challenges.

• Access to significant case history database

The Araldite® 2000 PLUS range can be used across a vast range of structural engineering applications. Sample case studies from our extensive library available on our website www.araldite2000plus.com.

• Additional reference guides available

Araldite® has been a leading adhesive brand for 60 years and our experience is reflected in our comprehensive technical support packages which can be accessed through our website and provide a complete solution to all adhesive processing and performance needs.



Distributed by

intertronics

17 Station Field Industrial Estate
Banbury Road
KIDLINGTON
Oxfordshire, OX5 1JD
Tel: 01865 842842 Fax: 01865 842172
e-mail: enquiries@intertronics.co.uk
www.intertronics.co.uk

All trademarks mentioned are either property of or licensed to Huntsman Corporation or an affiliate thereof.

Sales of the product described herein ("Product") are subject to the general terms and conditions of sale of either Huntsman Advanced Materials LLC, or its appropriate affiliate including without limitation Huntsman Advanced Materials (Europe) BVBA, Huntsman Advanced Materials Americas Inc., or Huntsman Advanced Materials (Hong Kong) Ltd. ("Huntsman"). The following supercedes Buyer's documents.

While the information and recommendations included in this publication are, to the best of Huntsman's knowledge, accurate as of the date of publication, NOTHING CONTAINED HEREIN IS TO BE CONSTRUED AS A REPRESENTATION OR WARRANTY OF ANY KIND, EXPRESS OR IMPLIED, INCLUDING BUT NOT LIMITED TO ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, NON-INFRINGEMENT OF ANY INTELLECTUAL PROPERTY RIGHTS, OR WARRANTIES AS TO QUALITY OR CORRESPONDENCE WITH PRIOR DESCRIPTION OR SAMPLE, AND THE BUYER ASSUMES ALL RISK AND LIABILITY WHATSOEVER RESULTING FROM THE USE OF SUCH PRODUCT, WHETHER USED SINGLY OR IN COMBINATION WITH OTHER SUBSTANCES. No statements or recommendations made herein are to be construed as a representation about the suitability of any Product for the particular application of Buyer or user or as an inducement to infringe any patent or other intellectual property right. Data and results are based on controlled conditions and/or lab work. Buyer is responsible to determine the applicability of such information and recommendations and the suitability of any Product for its own particular purpose, and to ensure that its intended use of the Product does not infringe any intellectual property rights.

The Product may be or become hazardous. Buyer should (i) obtain Material Safety Data Sheets and Technical Data Sheets from Huntsman containing detailed information on Product hazards and toxicity, together with proper shipping, handling and storage procedures for the Product, (ii) take all steps necessary to adequately inform, warn and familiarize its employees, agents, direct and indirect customers and contractors who may handle or be exposed to the Product of all hazards pertaining to and proper procedures for safe handling, use, storage, transportation and disposal of and exposure to the Product and (iii) comply with and ensure that its employees, agents, direct and indirect customers and contractors who may handle or be exposed to the Product comply with all safety information contained in the applicable Material Safety Data Sheets, Technical Data Sheets or other instructions provided by Huntsman and all applicable laws, regulations and standards relating to the handling, use, storage, distribution and disposal of and exposure to the Product.

Please note that products may differ from country to country. If you have any queries, kindly contact your local Huntsman representative.

© 2007 Huntsman Corporation. All rights reserved.

www.araldite2000plus.com

HUNTSMAN

Enriching lives through innovation

EUROPE / AFRICA

Huntsman Advanced Materials
(Switzerland) GmbH
Klybeckstrasse 200
P.O. Box
4002 Basel
Switzerland
Tel +41 61 966 41 20
Fax +41 61 966 35 19

INDIA / MIDDLE EAST

Huntsman Advanced Materials
(India) Pvt. Ltd
5th Floor, Bldg. No. 10
Solitaire Corporate Park
167, Guru Hargovindji Marg, Chakal
Andheri (East)
Mumbai - 400 093
India
Tel +91 22 4095 1556 - 60
Fax +91 22 4095 1300/1400/1500

ASIA / PACIFIC

Huntsman Advanced Materials
(Hong Kong) Ltd
Suites 3 - 12, Level 41
Langham Place
8 Argyle Street
Kowloon
Hong Kong
Tel +852 2148 8800
Fax +852 2424 1741

AMERICAS

Huntsman Advanced Materials
Americas Inc.
10003 Woodloch Forest Drive
The Woodlands,
Texas 77380
USA
Tel +1 888 564 9318
Fax +1 281 719 4047

More detailed information about these products can be found on our website: www.araldite2000plus.com

For any other information, please send an e-mail to: araldite2000plus@huntsman.com

Ref.Nr. CCA Araldite2000plus Plastics 04.07_EN

Design: www.zygmund.fr


Araldite®
2000+
Strength in bonding

HUNTSMAN

Enriching lives through innovation

adhere™
from intertronics

bonding **plastics**
to plastics and dissimilar substrates



The appropriate solution for Bonding plastics to any substrates

Huntsman's recognised expertise in research and development allows us to offer a uniquely wide range of innovative solutions all of which are backed by strong technical support and excellent levels of customer service. Araldite® 2000 PLUS adhesives are designed to satisfy all your plastic bonding requirements.

	2011		2010-1		2012		2013		2014-1*		2015				2021			2022		2047**		2018			2040		2041-1		2055	
	Multi purpose	Rapid cure		Chemical/temperature resistance		Toughened				Flexible			Rigid																	
Chemical type	EP	EP	EP	EP	EP	EP	MMA	MMA	MMA	PUR	PUR	PUR	PUR	PUR	PUR	PUR	PUR	PUR	PUR	PUR	PUR	PUR	PUR	PUR	PUR	PUR	PUR	PUR		
Fast curing		■	■				■	■	■																					
Gap filling				■	■	■	■	■	■	■	■	■	■	■	■	■	■	■	■	■	■	■	■	■	■	■	■	■		

BONDING PLASTICS TO PLASTICS

	2011	2010-1	2012	2013	2014-1*	2015	2021	2022	2047**	2018	2040	2041-1	2055
GRP	●	○	●	●	●	●	●	●	○	●	●	●	●
CFRP	●	●	●	●	●	●	●	●	○	○	○	●	○
SMC	●	○	○	●	●	●	○	○	○	●	○	●	●
ABS	●	○	○	○	○	○	○	○	○	○	○	○	○
PVC	○	○	○	○	○	○	○	○	○	○	○	○	○
PMMA	○	○	○	○	○	○	○	○	○	○	○	○	○
Polycarbonate	○	○	○	○	○	○	○	○	○	○	○	○	○
Polyamides	●	○	○	○	○	○	○	○	○	○	○	○	○

BONDING PLASTICS TO METALS

	2011	2010-1	2012	2013	2014-1*	2015	2021	2022	2047**	2018	2040	2041-1	2055
Ferrous metals	●	○	●	●	●	●	●	●	○	○	○	○	○
Stainless steel	●	●	●	●	●	●	●	●	○	○	○	○	○
Aluminium	●	●	●	●	●	●	●	●	○	○	○	○	○
Copper	●	●	●	●	●	●	●	○	○	○	○	○	○
Brass	●	●	●	●	●	●	●	○	○	○	○	○	○
Zinc/Galvanised metal	●	●	○	●	●	○	○	○	○	○	○	○	○

BONDING PLASTICS TO NON METALS

	2011	2010-1	2012	2013	2014-1*	2015	2021	2022	2047**	2018	2040	2041-1	2055
Rubbers	○	○	○	○	○	○	○	○	○	○	○	○	○
Glass	○	○	○	○	○	○	○	○	○	○	○	○	○
Ceramics	●	○	●	●	○	○	○	○	○	○	○	○	○
Wood	●	●	●	●	●	●	○	○	○	○	○	○	○

EP Epoxy / MMA Methyl Methacrylate / PUR Polyurethane • ● Excellent / ○ Good / ○ Moderate



Processing, performance and packaging data

Araldite® 2000 PLUS is a trusted brand – with more than 60 years experience in developing engineering adhesives.



Bonding plastics	Multi purpose		Rapid cure		Chemical / temperature resistance		Toughened				Flexible			Rigid
	2011	2010-1	2012	2013	2014-1*	2015	2021	2022	2047**	2018	2040	2041-1	2055	
Chemical type	EP	EP	EP	EP	EP	EP	MMA	MMA	MMA	PUR	PUR	PUR	PUR	
Product description	<ul style="list-style-type: none"> Multi purpose Long working life Low shrinkage 	<ul style="list-style-type: none"> Fast curing Toughened Low shrinkage 	<ul style="list-style-type: none"> Fast curing General purpose Low shrinkage 	<ul style="list-style-type: none"> Metal coloured paste Suitable for vertical applications Low shrinkage 	<ul style="list-style-type: none"> Grey paste High temperature and chemical resistance Low shrinkage 	<ul style="list-style-type: none"> Toughened paste Ideal for GRP, SMC and dissimilar substrates Low shrinkage 	<ul style="list-style-type: none"> Rapid curing High peel strength Multi purpose 	<ul style="list-style-type: none"> Good sanding properties Ideal for bonding thermoplastics 	<ul style="list-style-type: none"> Gap filling Requires minimal surface treatment 	<ul style="list-style-type: none"> Good UV stability Ideal for bonding thermoplastics Low shrinkage 	<ul style="list-style-type: none"> Ideal for bonding plastics Low shrinkage Ideal for thick bond lines 	<ul style="list-style-type: none"> Black colour Ideal for bonding plastics especially SMC or polyamides Low shrinkage 	<ul style="list-style-type: none"> Gap filling Long open time Resists weathering and humidity Low shrinkage 	

PROCESSING DATA

	2011	2010-1	2012	2013	2014-1*	2015	2021	2022	2047**	2018	2040	2041-1	2055
Viscosity (at 23°C)	30-45 Pa.s	Apr. 80 Pa.s	25-35 Pa.s	Thixotropic	Thixotropic	Thixotropic	Apr. 45 Pa.s	Apr. 60 Pa.s	Apr. 70 Pa.s	Apr. 8 Pa.s	Apr. 50 Pa.s	Apr. 55 Pa.s	Thixotropic
Useable life of adhesive (at 23°C)													
In mixer nozzle	1.8 hr	10 min	8 min	1.3 hr	1 hr	40 min	3 min	10 min	5 min	40 min	15 min	15 min	45 min
100 g of mix	1.5 hr	6 min	5 min	60 min	1 hr	40 min	-	-	-	40 min	15 min	15 min	60 min
Time required to reach (at 23°C)													
Light handling strength (1 MPa)	7 hr	30 min	20 min	4 hr	3 hr	4 hr	8 min	18 min	5 min	4 hr	6 hr	3 hr	6 hr
50% of final shear strength	10 hr	3 hr	1 hr	10 hr	5 hr	6 hr	20 min	30 min	20 min	10 hr	20 hr	16 hr	20 hr
Time required to reach (at 60°C)													
50% of final shear strength	45 min	20 min	10 min	40 min	20 min	40 min	-	-	-	30 min	1.5 hr	60 min	60 min

PERFORMANCE DATA

	2011	2010-1	2012	2013	2014-1*	2015	2021	2022	2047**	2018	2040	2041-1	2055
Lap shear strength on GRP substrate	11 MPa	5 MPa	9 MPa	8 MPa	9 MPa	9 MPa	8 MPa	8 MPa	6 MPa	8 MPa	7 MPa	8 MPa	9 MPa
Peel strength on Al substrate	5 N/mm	6 N/mm	5.5 N/mm	4 N/mm	3 N/mm	4 N/mm	11 N/mm	4 N/mm	3 N/mm	4 N/mm	4 N/mm	6 N/mm	1 N/mm
Typical Tg / Max temp giving LSS of 5 MPa	45°C / 90°C	40°C / 80°C	40°C / 80°C	45°C / 70°C	85°C / 140°C	65°C / 110°C	65°C / 110°C	45°C / 100°C	80°C / 90°C	Flex / 40°C	30°C / 50°C	30°C / 50°C	60°C / 90°C
Resistance properties													
Chemical	○	○	○	●	●	○	○	●	●	○	○	○	○
Heat	○	○	○	○	○	○	○	○	○	○	○	○	○
Water	○	○	○	○	○	○	○	○	○	○	○	○	○
Impact	●	●	○	○	○	○	○	○	○	○	○	○	○

PACKAGING

	2011	2010-1	2012	2013	2014-1*	2015	2021	2022	2047**	2018	2040	2041-1	2055
Cartridges													
50 ml	■	■	■	■	■	■	■	■	■	■	■	■	■
200 ml	■	■	■	■	■	■	■	■	■	■	■	■	■
400 ml													
500 ml													
Working packs (2 kg kits)	■		■	■	■	■							

* Araldite® 2014-1 is only registered for use in Europe. Araldite 2014® is directly equivalent in performance to 2014-1 and is available for regions outside of Europe.

** Araldite® 2047 is currently only registered for use in Europe.